


# EPDiC17

Šibenik.Croatia. 31 May - 3 June 2022.



**EPDiC17 BOOK OF ABSTRACTS**



The European Powder Diffraction Conference

Šibenik, Croatia, 31 May – 03 June 2022

# Book of Abstracts

editors

Jasminka Popović

Zoran Štefanić

published by

Croatian Association of Crystallographers

Zagreb, 25 May 2022

## Photocatalytic and antimicrobial effects of zinc oxide nanoparticles prepared by thermal decomposition of zinc benzenepolycarboxylato complexes

Jelena Rogan<sup>1</sup>, Lidija Radovanović<sup>2</sup>, Bojana Simović<sup>3</sup>, Željko Radovanović<sup>2</sup>, Katarina Mihajlovski<sup>1</sup> and Aleksandra Dapčević<sup>1</sup>

1. Faculty of Technology and Metallurgy, University of Belgrade, Karnegijeva 4, Belgrade, Serbia

2. Innovation Center-Faculty of Technology and Metallurgy, University of Belgrade, Karnegijeva 4, Belgrade, Serbia

3. Institute for Multidisciplinary Research, University of Belgrade, Kneza Višeslava 1, Belgrade, Serbia

✉ rogan@tmf.bg.ac.rs

Zinc oxide nanoparticles (ZnO-NPs) have been a subject of numerous researches owing to their multifunctional properties in many applications, such as solar cells, UV light-emitting devices, gas sensors and photocatalysts. ZnO-NPs can be synthesized through various methods and their features can be tailored by shape and size, resulting in new applications relevant to their structural properties.

The synthesis of ZnO-NPs *via* controlled thermal decomposition of the single-source precursors represents a novel synthetic methodology. The basic goal of this study was to investigate the influence of precursors on crystallite size and morphology of the resulting ZnO-NPs. Four structurally characterized Zn complexes with different benzenepolycarboxylato ligands [1] were used as precursors for investigation of photocatalytic and antimicrobial effects of thermally obtained ZnO-NPs.

The XRPD and FESEM analysis of ZnO-NPs, prepared by thermolysis of Zn precursors at 450 °C in the air atmosphere, revealed hexagonal wurtzite structure (space group  $P6_3mc$ ,  $a \approx 3.25$  and  $c \approx 5.21$  Å) with an average crystallite size in the range of 39–47 nm and similar morphology. The best photocatalytic activity for degradation of *Reactive orange 16* dye has been observed for ZnO-NPs where crystallites form the smallest agglomerates. All obtained ZnO-NPs showed excellent inhibitory effect against Gram-positive bacteria *Staphylococcus aureus* and Gram-negative bacteria *Escherichia coli*.

[1] L. Radovanović, J. Rogan, D. Poleti, M. Milutinović, M.V. Rodić, *Polyhedron* **112** (2016) 18.